

ORAGUARD® 250AS

Laminating Film

Short description

Special PVC film transparent, with embossed surface (anti-slip structure)

Front material

Soft PVC Film, 0.12 mm

Liner

One-sided siliconized kraft paper, 90 g/m²

Adhesive

Solvent-polyacrylate, permanent, Transparent, 0.024 mm

Technical properties

RESISTANCE

Durability	with horizontal orientation, Central European normal climate	
	2 Year(s)	with horizontal alignment, central European normal climate, without tread load, exterior
	5 Year(s)	with horizontal alignment, central European normal climate, without tread load, interior
	6 month	with horizontal alignment, central European normal climate, with tread load 7 months (depending on degree of stress)
Shelf Life	2 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Resistance to solvents and chemicals	Weak acids, Hydrochloric acid (10 %), Water, Isopropyl alcohol, Washing suds (0.5 % household cleaner)	At room temperature
Maximum shrinkage	Maximum shrinkage along 0.4 mm Maximum shrinkage across 0.4 mm	

ORAGUARD® 250AS

Laminating Film

Elongation at break	Minimum elongation at break along 130 %	DIN EN ISO 527
	Minimum elongation at break across 150 %	
Tensile strength	Minimum tensile strength along 19 N/mm ²	DIN EN ISO 527
	Minimum tensile strength across 19 N/mm ²	
Temperature resistance	Minimum temperature -40 °C Maximum temperature 60 °C	Bonded to aluminum, short-term load

ADHESIVE PROPERTIES

Adhesive power	12 N/25 mm	after 24 h, on stainless steel, average value FINAT TM 1
----------------	------------	--

PROCESSING

Application temperature	Minimum temperature 10 °C
-------------------------	---------------------------

PRODUCT NOTE

Due to the diversity of prints and printing techniques, the user should test the suitability of ORAGUARD® laminating films for the specific print purpose, prior to use. Furthermore the application information published by ORAFOL must be followed.

IMPORTANT NOTES

All ORAGUARD® products are subject to careful quality control during the entire manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORAGUARD® products is based on research results which the company believes to be reliable, but which do not constitute a guarantee. Because of the wide variety of uses of ORAGUARD® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice.